



### KLINGERSIL® C-4201

Sealing material for applications in oil, solvent, water, low temperature steam and other chemicals in general.

**Material** Sealing material with aramid fibers bonded with NBR rubber.

**Color** Green /Green

**Sizes** 2000x1500mm | 4000x1500mm


**Thicknesses** 0,4 mm - 6,4mm



### Technical Data - Typical values \* thickness for 1.5mm

<b>Compressibility ASTM F 36 A</b>		%	15
<b>Recovery ASTM F 36 A</b>		%	55
<b>Heat loss DIN 52911</b>		%	25
<b>Stress relaxation BS 7531</b>	40 Mpa / 200°C	Mpa	20
<b>KLINGER hot compression 50 Mpa</b>	Thickness decrease at 23°C	%	16
	Thickness decrease at 200°C	%	26
<b>Thickness increase after fluid (ASTM F 146)</b>	Oil ASTM N° 3: 5h a 150°C	%	5
	Fuel B: 5h a 23°C	%	7
<b>Weight increase after fluid (ASTM F 146)</b>	Oil ASTM N° 3: 5h a 150°C	%	13
	Fuel B: 5h a 23°C	%	13
<b>Density</b>		g/cm3	1,7

\* Reference numbers between allowed value ranges. For information on the value ranges, contact us.



### Pressure and Temperature Chart

- ① If the temperature and pressure of your application are in this area, technical assessment is not necessary.
- ② If the temperature and pressure of your application are in this area, a technical assessment is recommended.
- ③ If the temperature and pressure of your application are in this area, a rigorous technical assessment must be carried out.